



POLYVINYL CHLORIDE P-190 GP

Producer: Grupo Primex, S.A. / Mexico

PROPERTIES	UNITS	MIN	MAX	PRIMEX METHOD	REFERENCE METHOD
K-Value *&		58	60	ACA-I-018	Din 53726-1983
Apparent Bulk Density *&	g/cc	0,53		ACA-I-005	ASTM D 1895 B-96
Contamination &			35/0 ⁽¹⁾	ACA-I-002	
Volatile matter * &	% Peso		0 3	ACA-I-006	ASTM D 3030-95
Particle Size					
Distribution *&	Retained % Weight		Traces ⁽²⁾	ACA-I-008	ASTM D 1921-A-96
Sieve 40			5.0		
Sieve 60					
Through					
Sieve 200			7.0		
Oven Heat *&					
Stability	%	90		ACA-I-004	ASTM D 2115-67