



POLYVINYL CHLORIDE PETVINIL S65/R68

Producer: Petkim Petrokimya Holding A.S. / Turkey

Applications: Rigid pipes.

PROPERTIES	UNIT	VALUE	TEST METHOD
Guaranteed values			
Viscosity Index (In Cyclohexanone At 25°C)	cm ³ /g	109.0-122.0	SOLVAY 1A/93
K Value (In Cyclohexanone At 25°C)	-	66-70	SOLVAY 1A/93
Apparent Bulk Density	g/cm ³	0.52-0.60	SOLVAY 4A/91
Screen Analysis:			
Retained on 0.250 mm sieve	% wt	Max.8	SOLVAY 8A/92, 8F/92
Retained on 0.063 mm sieve	% wt	Min. 90	SOLVAY 8A/92, 8F/92
Volatiles	% wt	Max.0.5	SOLVAY 2A/90
Impurities	piece/ft ²	Max.60	SOLVAY 6A/92

Packing: In 25 kgs Form Fill Sealed white colored PE bags , loose or palletized and shrinkwrapped or in 1400 kgs big bags

Storage conditions: Storage in closed and dry areas is recommended.

Note: This grade has certificate for production of material in contact with foodstuffs as received by Ministry of Agriculture and Village Affairs dated 21.02.2007 and no. 35-00214-00005-1.